1880

Weekly Report of Gold Deposits Melted at United States Mint.

Date.	Assay No.	Name of Depositor.	Weight before Melting. OZ.	DEC.	Weight after Melting. OZ.	DEC.	Loss. OZ.	DEC.	Loss per ct.	Gain. OZ.	DEC.	Description of Bullion.
Jany 26th	224	G. C. Thompson	11	23	9	21	2	02	18 36			Jewelry & Wtch Cases
	5	Drexel & Co.	8	60	8	28		32	3 56			Aml, Grs & Lps, Va.
	6	W. H. Lee	82	48	82	41		07	08			Bars
	7	J. L. Nelms	26	86	26	86						U. S. Coin
27th	8	G. C. Thompson	20	01	19	35		66	3 30			Wtch Cases & Jewelry
	9	Do	8	68	7	94		74	8 22			Jewelry, &c. Dirty
	30	Do	29	07	28	57		50	1 72			Jewelry, Wtch Cases & Silver
	1	Do	14	62	11	68	2	94	19 60			Jewelry & Wtch Cases
28th	2	Wood, Marsh & Co.	5	50	5	36		14	2 80			Aml & Grs, N. C.
	3	John Stuertz	8	91	8	90		01	11			Buttons
	4	R. H. Bansley	13	42	13	41		01	07			Button
	5	J. C. Meeks	26	87	26	87						Coin
	6	Hastings & Co.	15	37	12	25	3	12	20 80			Leaf
	7	Phillips & Jacobs	53	73	53	73						U. S. Coin
	8	G. C. Thompson	8	81	6	84	1	97	21 89			Buttons (Base) & Wtch Cases
	9	F. H. Lyon	10	97	10	95		02	18			For. Coin & Jewelry
29th	40	G. C. Thompson	45	15	39	02	6	13	13 62			Rings, Base
	1	Morgan & Headly	53	89	46	84	7	05	13 06			Sweeps, Filings & Bar
	2	Carrow, Bishop & Co.	10	95	10	93		02	18			Bars
30th	3	G. C. Thompson	8	67	8	18		49	5 44			Wtch Cases & Jewelry
	4	Do	5	43	5	20		23	4 60			Aml & Grs, Geo.
	5	Do	25	58	23	58	2	00	7 69			Wtch Case, Jewelry & Silver
	6	Do	126	59	86	45	40	14	31 61			Ring, Base
	7	Do	22	99	17	58	5	41	23 52			Ring, Base
	8	Do	9	29	9	26		03	33			Button, N. C.
	9	F. H. Lyon	6	47	6	47						For. & U. S. Coin
31st	50	G. C. Thompson	4	86	4	86						Melted Sps, Va
	1	Do	5	37	5	37						Melted Sps, Va.
	2	Wm Simpson, Sons & Co.	6	14	5	99		15	2 50			Crushed Quartz
	3	J. Bedichimer	54	78	52	52	2	26	4 11			Bars & Silver
	4	J. C. White	13	37	12	99		38	2 92			S. H. Button, Filings, &c.
	5	G. C. Thompson	11	62	7	77	3	85	32 08			Bars, Base
			756	28	671	62	84	66	13 40			

Notes of Melter & Refiner.

3/2/80

The deposits are from the following sources:

Virginia	(2)	3
N. Carolina	(1)	2
Georgia		1
Finer bullion	(3)	5
Baser		7
Jewelry, Cases, &c		6
very base bullion		5
Coin		4
Total		33

The average loss in melting the very base bullion, 25.98 %, is even moderate; the Jewelry & Cases, 11.42 % is a fair medium, rather lower than usual; the baser, 5¾ %, is a fair result; and the finer bullion, 0.12 % is low. The loss on the mixt metal of Virginia 3.56 %, of N. Carolina 2.80 %, & of Georgia, 4.60 %, is in each case a proper ratio. The 4 deposits of coin lost nothing, rather lower than it should be.

Ja C Booth
M. & R.

For week ending Jany 31st 1880
Approximate value, $ 10,410,11

of the Mint.

J. Robley Dunglison Register.

RG104 E-1 Box 120

Report of Gold Deposits
melted for week ending
January 31st 1880

RG104 E-1 Box 120

NARA RG104, Entry 1, Box 120

[Abstract:] Report of Gold Deposits melted for week ending January 31, 1880

Weekly Report of Gold Deposits Melted at United States Mint.

[Please see original images for data table.]